



IK Copy

Physical Properties			
<i>Description</i>	<i>Unit</i>	<i>Test Reference</i>	
<i>Basis Weight</i>	gr / m ²	T 410 OM - 08	80 ± 4%
<i>Thickness</i>	µm	T 411 OM - 10	106 ± 4
<i>Moisture Content</i>	%	T 412 OM - 11	3.8 - 5.0
<i>Opacity</i>	%	ISO 2471	≥ 90.0
<i>Roughness</i> <i>W</i>	sec/10ml	T 479 OM - 09	≤ 220
<i>F</i>			≤ 220
<i>Stiffness</i> MD	m/Newton	T 535 WD - 03	≥ 0.40
CD			≥ 0.20
Optical Properties			
Brightness	%	ISO 2470	95.0 ± 1
CIE Whiteness	%	ISO 11476	160.0 ± 3

APPLICATION LASER/INKJET 100 % PLANTATION 100 % ECF PULP	ISO 9001 : Quality control ISO 14001 : Environmental protection ISO 9706 : Aging resistance
--	---

Mill: INDAH KIAT
 Mill Update : Aprile 2016